



EVALUATION SUBJECT: TITEN TURBO™ SCREW ANCHORS FOR USE IN UNCRACKED CONCRETE

REPORT HOLDER:

Simpson Strong-Tie Company Inc.
5956 West Las Positas Boulevard
Pleasanton, California 94588
(800) 999-5099
www.strongtie.com

CSI Section:

03 15 19 Cast-in Concrete Anchors
05 05 19 Post-installed Concrete Anchors

1.0 SCOPE OF EVALUATION

1.1 Compliance to the following codes & regulations:

- 2018, 2015, 2012, 2009 and 2006 International Building Code® (IBC)
- 2018, 2015, 2012, 2009 and 2006 International Residential Code® (IRC)
- 2020 City of Los Angeles Building Code (LABC) – attached supplement
- 2020 City of Los Angeles Residential Code (LARC) – attached supplement

1.2 Evaluated in accordance with:

- ICC-ES Acceptance Criteria for Mechanical Anchors in Concrete Elements (AC193)

1.3 Properties assessed:

- Structural

2.0 PRODUCT USE

Simpson Strong-Tie® Titen Turbo™ Screw Anchors are used to resist static and wind tension and shear loads in uncracked normal-weight concrete having a specified compressive strength, f'_c , of 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa). The anchoring system is an alternative to anchors described in Section [1901.3](#) of the 2018, 2015 IBC, Sections [1908](#) and [1909](#) of the 2012 IBC, and Sections [1911](#) and [1912](#) of the 2009 and 2006 IBC. The anchors may also be used where an engineered design is submitted in accordance with Section [R301.1.3](#) of the IRC.

3.0 PRODUCT DESCRIPTION

3.1 Titen Turbo™ Screw Anchors: The Titen Turbo™ Screw Anchors are post-installed anchors that derive their holding strength from the mechanical interlock of the screw anchor threads with the grooves cut into the concrete by the screw anchor during installation.

The screw anchors are manufactured from carbon steel that is given a supplementary hardening process. The screw anchors are available in nominal sizes of $\frac{3}{16}$ inch and $\frac{1}{4}$ inch (4.8 mm and 6.4 mm) and in a variety of lengths. The Titen Turbo™ Screw Anchors are available with either a slotted hex head or a Philips flat head as shown in [Figure 1 of this report](#). All Titen Turbo™ Screw Anchors are provided with zinc plating and baked ceramic coating.

3.2 Concrete

Normal-weight and light-weight concrete shall conform to Sections [1901](#) and [1903](#) of the 2018, 2015 and 2012 IBC or Section [1903](#) and [1905](#) of the 2009 and 2006 IBC. The specified compressive strength of the concrete, f'_c , shall be from 2,500 psi to 8,500 psi (17.2 MPa to 58.6 MPa).

4.0 DESIGN AND INSTALLATION

4.1 Strength Design

4.1.1 General: The design strength of anchors under the 2018 and 2015 IBC and Section R301.1.3 of the 2018 and 2015 IRC shall be determined in accordance with [ACI 318-14](#) as amended in IBC Section [1905](#) and this report. The design strength of anchors under the 2012, 2009 and 2006 IBC and Section [R301.1.3](#) of the 2012, 2009 and 2006 IRC shall be determined in accordance with [ACI 318-11](#) Appendix D and this report.

Design parameters are based on ACI 318-14 for use with the 2018 and 2015 IBC and ACI 318-11 for use with the 2012, 2009 and 2006 IBC unless noted otherwise in Sections 4.1.1 through [4.1.11](#) of this report.

The strength design of anchors shall conform to the requirements of ACI 318-14 Section 17.3.1 except as required for seismic design in ACI 318-14 Section 17.2.3; or ACI 318-11 Section D.4.1, except as required for seismic design in ACI 318-11 Section D.3.3.

Strength reduction factors, ϕ , described in ACI 318-14 Section 17.3.3 or ACI 318-11 Section D.4.3, and noted in [Tables 3](#) and [4](#) of this report, shall be used for load combinations calculated in accordance with Section [1605.2](#) of the 2018, 2015, 2012, 2009 or 2006 IBC, ACI 318-14 Section 5.3, and ACI 318-11 Section 9.2. Strength reduction factors, ϕ , described in ACI 318-11 Section D.4.4 shall be used for load combinations calculated in accordance with Appendix C of ACI 318-11. Construction documents shall include information specified in ACI 318-14 Sections 17.7.7 and 26.7, or ACI 318-11 Sections 1.2 and D.8.7.





4.1.2 Static Steel Strength in Tension: The nominal steel strength of a single anchor in tension, N_{sa} , in accordance with ACI 318-14 Section 17.4.1.2 or ACI 318-11 Section D5.1.2, and the corresponding strength reduction factors, ϕ , corresponding to a brittle steel element in accordance with ACI 318-14 Section 17.3.3, or ACI 318-11 Section D.4.3, are provided in [Table 3](#) of this report for each anchor type referenced in this report.

4.1.3 Static Concrete Breakout Strength in Tension: The nominal static concrete breakout strength of a single anchor or group of anchors in tension, N_{cb} or N_{cbg} , shall be calculated in accordance with ACI 318-14 Section 17.4.2 or ACI 318-11 Section D.5.2. The nominal concrete breakout strength in tension in regions of the concrete where analysis indicates no cracking in accordance with ACI 318-14 Section 17.4.2.6 or ACI 318-11 Section D.5.2.6, shall be calculated using k_{un-cr} given in [Table 3](#) and where $\Psi_{c,N} = 1.0$. The value of f'_c used for calculation purposes shall be limited to 8,000 psi (55.1 MPa) maximum in accordance with ACI 318-14 Section 17.2.7 or ACI 318-11 Section D.3.7.

4.1.4 Static Pullout Strength in Tension: The nominal pullout strength of a single anchor in tension in accordance with ACI 318-14 Sections 17.4.3.1 and 17.4.3.2 or ACI 318-11 Sections D.5.3.1 and D.5.3.2 in uncracked concrete, $N_{p,un-cr}$, is given in [Table 3](#) of this report. For all design cases, $\Psi_{c,p} = 1.0$. The nominal pullout strength may be adjusted for concrete strengths as follows:

$$\text{For } 3/16'' \text{ anchors: } N_{p, f'c} = N_{p,un-cr}(f'_c/2500)^{0.0}$$

$$\text{For SI: } N_{p, f'c} = N_{p,un-cr}(f'_c/17.2)^{0.0}$$

$$\text{For } 1/4'' \text{ anchors: } N_{p, f'c} = N_{p,un-cr}(f'_c/2500)^{0.23}$$

$$\text{For SI: } N_{p, f'c} = N_{p,un-cr}(f'_c/17.2)^{0.23}$$

Where f'_c is the specified concrete compression strength.

4.1.5 Static Steel Strength in Shear: The nominal static steel strength of a single anchor in shear as governed by the steel, V_{sa} , and the corresponding strength reduction factor for a brittle steel element, ϕ , complying with ACI 318-14 Sections 17.5.1.2 and 17.3.3 or ACI 318-11 Sections D.6.1.2 and D.4.3 respectively, are given in [Table 4](#) of this report and shall be used in lieu of the values derived by calculation from ACI 318-14 Eq. 17.5.1.2b or ACI 318-11 Eq. D-29.

4.1.6 Static Concrete Breakout Strength in Shear: The nominal static concrete breakout strength of a single anchor or group of anchors in shear, V_{cb} or V_{cbg} , shall be calculated in accordance with ACI 318-14 Section 17.5.2 or ACI 318-11 Section D.6.2, based on information given in [Table 4](#) of this report. The basic concrete breakout strength of a single anchor in shear, V_b , shall be calculated in accordance with ACI 318-14 Section 17.5.2.2 or ACI 318-11 Section D.6.2.2

using the values given in [Table 4](#) of this report. In addition, h_{ef} shall replace l_e in ACI 318-14 Eq. 17.5.2.2a or ACI 318-11 Eq. D-33 and in no case shall h_{ef} exceed $8d_a$. The value of f'_c used for calculation purposes shall be limited to 8,000 psi (55.1 MPa) maximum in accordance with ACI 318-14 Section 17.2.7 or ACI 318-11 Section D.3.7.

4.1.7 Static Concrete Pryout Strength in Shear: The nominal static pryout strength of a single anchor or group of anchors in shear, V_{cp} or V_{cpg} , shall be calculated in accordance with ACI 318-14 Section 17.5.3 or ACI 318-11 Section D.6.3, using the value of k_{cp} , described in [Table 4](#), and the values of N_{cb} or N_{cbg} , as calculated in Section 4.1.3 of this report.

4.1.8 Interaction of Tensile and Shear Forces: For designs that include combined tension and shear, the interaction of tension and shear loads shall be calculated in accordance with ACI 318-14 Section 17.6 or ACI 318-11 Section D.7.

4.1.9 Minimum Member Thickness h_{min} , Minimum Anchor Spacing, s_{min} , and Minimum Edge Distance, c_{min} : In lieu of ACI 318-14 Sections 17.7.1 and 17.7.3 or ACI 318-11 Sections D.8.1 and D.8.3, values of c_{min} and s_{min} used for anchor design and installation shall conform to the values provided in [Table 2](#) of this report. In lieu of ACI 318-14 Section 17.7.5 or ACI 318-11 Section D.8.5, the minimum member thicknesses, h_{min} , shall be in accordance with [Table 2](#) of this report.

4.1.10 Critical Edge Distance, c_{ac} : In applications where $c < c_{ac}$ and supplemental reinforcement to control splitting of the concrete is not present, the concrete breakout strength in tension for uncracked concrete, calculated in accordance with ACI 318-14 Section 17.4.2 or ACI 318-11 Section D.5.2 shall be further multiplied by the factor $\Psi_{cp,N}$ as follows:

$$\Psi_{cp,N} = c/c_{ac}$$

whereby the factor $\Psi_{cp,N}$ need not be taken as less than $1.5h_{ef}/c_{ac}$. For all other cases, $\Psi_{cp,N} = 1.0$. In lieu of ACI 318-14 Section 17.7.6 or ACI 318-11 Section D.8.6, the values for critical edge distance, c_{ac} , shall be taken from [Table 2](#) of this report.

4.1.11 Lightweight Concrete: For the use of anchors in lightweight concrete, the modification factor λ_a equal to 0.8 λ is applied to all values of $\sqrt{f'_c}$ affecting N_n and V_n where λ is determined in accordance with ACI 318-08 (2009 IBC/IRC), ACI 318-11 (2012 IBC/IRC), and ACI 318-14 (2018, 2015 IBC/IRC). For ACI 318-05 (2006 IBC/IRC), λ shall be taken as 0.75 for all lightweight concrete and 0.85 for sand-lightweight concrete. Linear interpolation shall be permitted if partial sand replacement is used. In addition, the pullout strength $N_{p,un-cr}$ shall be multiplied by the modification factor, λ_a , as applicable.



$$T_{\text{applied}}/T_{\text{allowable, ASD}} + V_{\text{applied}}/V_{\text{allowable, ASD}} \leq 1.2$$

Eq. (4-3)

4.2 Allowable Stress Design

4.2.1 General: For anchors designed using load combinations in accordance with IBC Section [1605.3](#), allowable loads shall be established using Eq. (4-1) or Eq.

(4-2), as follows:

$$T_{\text{allowable, ASD}} = \phi N_n / \alpha \quad \text{Eq. (4-1)}$$

$$V_{\text{allowable, ASD}} = \phi V_n / \alpha \quad \text{Eq. (4-2)}$$

Where:

$T_{\text{allowable, ASD}}$ = Allowable tension load (lb or kN)

$V_{\text{allowable, ASD}}$ = Allowable shear load (lb or kN)

ϕN_n = The lowest design strength of an anchor or anchor group in tension as determined in accordance with ACI 318-14 Chapter 17 or ACI 318-11 Appendix D as amended in Section [4.1](#) of this report.

ϕV_n = The lowest design strength of an anchor or anchor group in shear as determined in accordance with ACI 318-14 Chapter 17 or ACI 318-11 Appendix D as amended in Section [4.1](#) of this report.

α = Conversion factor calculated as a weighted average of the load factors for the controlling load combination. In addition, α shall include all applicable factors to account for non-ductile failure modes and required over-strength.

The requirements for member thickness, edge distance and spacing, described in [Table 2](#) of this report, shall apply.

4.2.2 Interaction of Tensile and Shear Forces: In lieu of ACI 318-14 Sections 17.6.1, 17.6.2 and 17.6.3 or ACI 318-11 Sections D.7.1, D.7.2 and D.7.3, interaction of tension and shear loads shall be calculated as follows:

17.6.1 (D.7.1): If $V_{\text{applied}} \leq 0.2 V_{\text{allowable, ASD}}$ for the governing strength in shear, then the full allowable strength in tension, $T_{\text{allowable, ASD}}$, shall be permitted.

17.6.2 (D.7.2): If $T_{\text{applied}} \leq 0.2 T_{\text{allowable, ASD}}$ for the governing strength in tension, then the full allowable strength in shear, $V_{\text{allowable, ASD}}$, shall be permitted.

17.6.3 (D.7.3): If $V_{\text{applied}} > 0.2 V_{\text{allowable, ASD}}$ for the governing strength in shear and $T_{\text{applied}} > 0.2 T_{\text{allowable, ASD}}$ for the governing strength in tension, then:

4.3 Installation

Installation parameters are provided in [Table 2](#) of this report. The Titen Turbo™ Screw Anchors shall be installed in accordance with the manufacturer’s published instructions and this report. Screw anchor locations shall comply with this report and the plans and specifications approved by the building official. Screw anchors shall be installed in holes drilled using carbide-tipped drill bits conforming to [ANSI B212.15-1994](#) and [Table 2](#) of this report. The hole shall be drilled to the minimum depth noted in [Table 2](#) of this report. Dust and debris in the hole are not required to be removed prior to screw anchor installation. The screw anchor shall be driven into the predrilled hole using a cordless impact driver or cordless drill with a Titen Turbo™ drive adaptor.

4.4 Special Inspection

Special inspection is required in accordance with 2018, 2015 and 2012 IBC Sections [1705.1](#) and [1705.3](#), 2009 IBC Sections [1704.4](#) and [1704.15](#) or 2006 IBC Sections [1704.4](#) and [1704.13](#) and this report. The special inspector shall make periodic inspections during anchor installation to verify anchor type, anchor dimensions, concrete compressive strength, hole dimensions, drill bit size, anchor spacing, edge distances, concrete thickness, anchor embedment and adherence to the manufacturer’s published installation instructions. The special inspector shall be present as often as required in accordance with the “statement of inspection.”

5.0 LIMITATIONS

The Simpson Strong-Tie® Titen Turbo™ Screw Anchors described in this report are suitable alternatives to what is specified in the codes listed in Section [1.0](#) of this report, subject to the following limitations:

5.1 Titen Turbo™ Screw Anchors shall be installed in accordance with the manufacturer's published installation instructions and this report as shown in [Figure 2](#) of this report. Where conflicts between this report and the published installation instructions occur, the more restrictive shall prevail.

5.2 Screw anchor sizes, dimensions and minimum embedment depths are as set forth in this report.

5.3 The screw anchors shall be installed in uncracked normal-weight concrete and lightweight concrete having a specified compressive strength of $f'_c = 2,500$ psi to 8,500 psi (17.2 MPA to 58.6 MPA).



5.4 The values of f'_c used for calculation purposes shall not exceed 8,000 psi (55.1 MPa).

5.5 Screw anchors shall be installed in concrete base materials in holes predrilled with carbide-tipped drill bits complying with ANSI B212.15-1994 in accordance with the installation details shown in [Table 2](#) of this report.

5.6 Strength design values shall be established in accordance with Section [4.1](#) of this report.

5.7 Allowable design values shall be established in accordance with Section [4.2](#) of this report.

5.8 Minimum anchor spacing, minimum edge distance, minimum member thickness, critical spacing, and minimum critical edge distance shall comply with the values described in this report.

5.9 Prior to installation, calculations and details demonstrating compliance with this report shall be submitted to the building official. The calculations and details shall be prepared by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.

5.10 Since an evaluation criteria for evaluating data to determine the performance of anchors subjected to fatigue or shock loading is unavailable at this time, the use of these anchors under such conditions is beyond the scope of this report.

5.11 Screw anchors shall not be installed in regions of concrete where cracking has occurred or where analysis indicates cracking may occur ($f_t > f_{cr}$), subject to the conditions of this report.

5.12 Screw anchors may be used to resist short-term loads due to wind and to seismic load combinations limited to locations designated as Seismic Design Categories A and B under the IBC, subject to the conditions of this report.

5.13 Screw anchors shall not be used to support fire-resistive construction. Where not otherwise prohibited in the IBC or IRC, Titen Turbo™ Screw Anchors are permitted for installation in fire-resistive construction provided at least one of the following conditions are met.

- Anchors are used to resist wind or seismic forces only.
- Anchors that support gravity load-bearing structural elements are within a fire-resistive envelope or a fire-resistive membrane, are protected by approved fire-resistive materials, or have been evaluated for resistance to fire exposure in accordance with recognized standards.
- Anchors are used to support nonstructural elements.

5.14 Use of screw anchors is limited to dry, interior locations.

5.15 Screw anchors have been evaluated for reliability against brittle failure and found to be not significantly sensitive to stress-induced hydrogen embrittlement.

5.16 Special inspection shall be provided in accordance with Section [4.4](#) of this report.


5.17 Titen Turbo™ Screw Anchors are manufactured under an approved quality control program.

6.0 SUBSTANTIATING DATA

Data in accordance with the ICC-ES Acceptance Criteria for Mechanical Anchors in Concrete Elements (AC193), approved October 2017, editorially revised April 2018. Test reports are from laboratories in compliance with [ISC/IEC 17025](#).

7.0 IDENTIFICATION

7.1 Titen Turbo™ Screw Anchors are identified in the field by labels on the packaging, bearing the company name (Simpson Strong-Tie Company, Inc.), product name (Titen Turbo™), the anchor diameter and length, catalog number, either IAPMO UES Mark of Conformity as shown below, and the evaluation report number (ER-712). In addition, the ≠ symbol and a length identification code letter are stamped on the head of each screw anchor.



IAPMO UES ER-712

Brian Gerber, P.E., S.E.
Vice President, Technical Operations
Uniform Evaluation Service

Richard Beck, PE, CBO, MCP
Vice President, Uniform Evaluation Service

GP Russ Chaney
CEO, The IAPMO Group

For additional information about this evaluation report please visit www.uniform-es.org or email us at info@uniform-es.org



TABLE 1
LENGTH IDENTIFICATION HEAD MARKS ON TITEN TURBO™ SCREW ANCHORS
(CORRESPONDS TO ANCHOR LENGTH IN INCHES)

Length ID marking on head		-	A	B	C	D	E	F	G	H	I	J
Length of anchor (inch)	From	1	1½	2	2½	3	3½	4	4½	5	5½	6
	Up to, but not including	1½	2	2½	3	3½	4	4½	5	5½	6	6½

For SI: 1 inch = 25.4 mm

TABLE 2
TITEN TURBO™ SCREW ANCHOR INSTALLATION INFORMATION¹

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL SCREW ANCHOR DIAMETER (inch)	
			3/16	¼
Nominal Outside Diameter (shank)	$d_a(d_o)^2$	In	0.129	0.164
Drill Bit Diameter	d_{bit}	In	5/32	3/16
Nominal Embedment depth	h_{nom}	In	1¾	1¾
Effective Embedment depth	h_{ef}	In	1.25	1.20
Minimum Concrete Thickness	h_{min}	In	3¼	3¼
Critical Edge Distance	c_{ac}	In	3	3
Minimum Edge Distance	c_{min}	In	1¾	1¾
Minimum Spacing Distance	s_{min}	In	1	2
Minimum Hole Depth	h_{hole}	In	2¼	2¼
Maximum Installation Torque	$T_{inst,max}$	ft-lb	Not applicable ³	Not applicable ³
Maximum Impact Wrench Torque Rating	$T_{impact,max}$	ft-lb	Not applicable ³	Not applicable ³

For SI: 1 inch = 25.4 mm, 1 ft-lb = 1.36 N-m

¹The information presented in this table is to be used in conjunction with the design criteria of [ACI 318-14](#) Chapter 17 or [ACI 318-11](#) Appendix D, as applicable.²For the 2006 IBC, d_o replaces d_a .³Installation shall be performed with a Simpson Titen Turbo Drive Adaptor. Section [4.3](#) of this report provides additional information.



**TABLE 3
TITEN TURBO™ SCREW ANCHOR CHARACTERISTIC TENSION STRENGTH DESIGN VALUES¹**

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL SCREW ANCHOR DIAMETER (inch)	
			3/16	¼
Anchor Category	1, 2, or 3	-	1	1
Nominal Embedment Depth	h_{nom}	In	1 ³ / ₄	1 ³ / ₄
Steel Strength in Tension				
Minimum Specified Yield Strength	f_{ya}	psi	100,000	100,000
Minimum Specified Ultimate Strength	f_{uta}	psi	125,000	125,000
Effective Tensile Stress Area	A_{se}	in ²	0.0131	0.0211
Steel Strength in Tension	N_{sa}	lbf	1640	2640
Strength Reduction Factor – Steel Failure ²	ϕ_{sa}	-	0.65	0.65
Concrete Breakout in Tension				
Effective Embedment	h_{ef}	In	1.25	1.20
Critical Edge Distance	c_{ac}	In	3	3
Effectiveness Factor for Uncracked Concrete	k_{uncr}	-	24	24
Modification Factor	$\Psi_{c,N}$	-	1	1
Strength Reduction Factor-Concrete Breakout Failure ³	ϕ_{cb}	-	0.65	0.65
Pullout Strength in Tension				
Pullout Resistance in Uncracked Concrete ($f'_c=2500$ psi) ⁵	$N_{p,uncr}$	lbf	1515	1515
Strength Reduction Factor – Pullout Failure ⁴	ϕ_p	-	0.65	0.65

For SI: 1 inch = 25.4 mm, 1 lbf = 4.448 N, 1 psi = 6.895 kPa

¹The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

² The tabulated value of ϕ_{sa} applies when the load combinations of Section 1605.2 of the IBC, ACI 318-14 Section 5.3 or ACI 318-11 Section 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, the appropriate value of ϕ shall be determined in accordance with ACI 318-11 Section D.4.4.

³ The tabulated value of ϕ_{cb} applies when both the load combinations of Section 1605.2 of the IBC, ACI 318-14 Section 5.3 or ACI 318-11 Section 9.2 are used and the requirements of ACI 318-14 Section 17.3.3 (c) or ACI 318-11 Section D.4.3, as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate value of ϕ shall be determined in accordance with ACI 318-11 Section D.4.4 for Condition B.

⁴ The tabulated value of ϕ_p applies when both the load combinations of ACI 318-11 Section 9.2 are used and the requirement of ACI 318 Section D.4.4(c) for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate value of ϕ shall be determined in accordance with ACI 318-11 Section D.4.5(c) for Condition B.

⁵ The value of $N_{p,uncr}$ may be increased in accordance with Section 4.1.4 of this report.



**TABLE 4
TITEN TURBO™ SCREW ANCHOR CHARACTERISTIC SHEAR STRENGTH DESIGN VALUES¹**

CHARACTERISTIC	SYMBOL	UNITS	NOMINAL SCREW ANCHOR DIAMETER (inch)	
			3/16	1/4
Anchor Category	1, 2 or 3	-	1	1
Nominal Embedment Depth	h_{nom}	in	1 ^{3/4}	1 ^{3/4}
Steel Strength in Shear				
Steel Strength in Shear	V_{sa}	lbf	475	720
Strength Reduction Factor – Steel Failure ³	ϕ_{sa}	-	0.6	0.6
Concrete Breakout in Shear				
Load Bearing Length of Anchor in Shear	l_e	in	1.25	1.20
Nominal Outside Diameter (shank)	$d_a(d_o)^2$	in	0.129	0.164
Strength Reduction Factor – Concrete Breakout Failure ⁴	ϕ_{cb}	-	0.7	0.7
Concrete Pryout Strength in Shear				
Coefficient for Pryout Strength	K_{cp}	-	1.0	1.0
Strength Reduction Factor – Concrete Pryout Failure ⁴	ϕ_{cp}	-	0.7	0.7

For SI: 1 inch = 25.4 mm, 1 lbf = 4.448 N

¹ The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 Chapter 17 or ACI 318-11 Appendix D, as applicable.

² For the 2006 IBC, d_o replaces d_a .

³ The tabulated value of ϕ_{sa} applies when the load combinations of Section 1605.2 of the IBC, ACI 318-14 Section 5.3 or ACI 318-11 Section 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, the appropriate value of ϕ shall be determined in accordance with ACI 318-11 Section D.4.4.

⁴ The tabulated values of ϕ_{cb} and ϕ_{cp} apply when both the load combinations of Section 1605.2 of the IBC, ACI 318-14 Section 5.3 or ACI 318-11 Section 9.2 are used and the requirements of ACI 318-14 Section 17.3.3(c) or ACI 318-11 Section D.4.3, as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, the appropriate value of ϕ shall be determined in accordance with ACI 318-11 Section D.4.4 for Condition B.



Figure 1 - Titen Turbo™ Screw Anchors



Figure 2 – Installation Instructions for Titen Turbo™ Screw Anchors



CITY OF LOS ANGELES SUPPLEMENT

Simpson Strong-Tie Company Inc.
5956 West Las Positas Boulevard
Pleasanton, California 94588
(800) 925-5099
www.strongtie.com

TITEN TURBO™ SCREW ANCHORS FOR USE IN UNCRACKED CONCRETE

CSI Division:

03 00 00—CONCRETE
05 00 00—METALS

CSI Section:

03 16 00—Concrete Anchors
05 05 19—Post-installed Concrete Anchors

1.0 RECOGNITION

The Simpson Strong-Tie Titen Turbo™ Screw Anchors for Use in Uncracked Concrete as evaluated and represented in IAPMO UES Evaluation Report ER-712 and with changes as noted in this supplement is a satisfactory alternative for use in buildings built under the following codes (and regulations):

- 2020 City of Los Angeles Building Code (LABC)
- 2020 City of Los Angeles Residential Code (LARC)

2.0 LIMITATIONS

Use of the Simpson Strong-Tie Titen Turbo™ Screw Anchors for Use in Uncracked Concrete recognized in this report is subject to the following limitations:

2.1 The design, installation, conditions of use and identification of the Titen Turbo™ Screw Anchors shall be in accordance with the 2018 International Building Code or the 2018 International Residential Code, as applicable, as noted in ER-712.

2.2 Prior to installation, calculations and details demonstrating compliance with this approval report and the 2020 Los Angeles Building Code or 2020 Los Angeles Residential Code shall be submitted to the structural plan check section for review and approval. The calculations and details shall be prepared by a registered engineer, licensed in the State of California.

2.3 The design and installation of the Titen Turbo™ Screw Anchors shall be in accordance with LABC Chapters 16 and 17.

2.4 The allowable and strength design values listed in ER-712 are for fasteners only. Connected members shall be checked for their capacity (which may govern).

2.5 Periodic special inspection shall be provided by the Registered Deputy Inspector in accordance with Section 1705 of the 2020 LABC during installations of the Titen Turbo™ Screw anchors.

2.6 Under the LARC a design in accordance with Section R301.1.3 shall be submitted.

This supplement expires concurrently with ER-712.

For additional information about this evaluation report please visit www.uniform-es.org or email us at info@uniform-es.org



FLORIDA SUPPLEMENT

Simpson Strong-Tie Company Inc.
5956 West Las Positas Boulevard
Pleasanton, California 94588
(800) 925-5099
www.strongtie.com

TITEN TURBO™ SCREW ANCHORS FOR USE IN UNCRACKED CONCRETE

CSI Division:

- 03 00 00—CONCRETE
- 05 00 00—METALS

CSI Section:

- 03 16 00—Concrete Anchors
- 05 05 19—Post-installed Concrete Anchors

1.0 RECOGNITION

Simpson Strong-Tie Titen Turbo™ Screw Anchors for use in uncracked concrete recognized in ER-712 have been evaluated for use to resist dead, live, wind, and seismic tension and shear loads limited to locations designated as Seismic Design Categories A and B under the IBC. The structural performance properties of the Simpson Strong-Tie Titen Turbo™ Screw Anchors were evaluated for compliance with the following codes:

- 2020 and 2017 Florida Building Code, Building (FBC--Building)
- 2020 and 2017 Florida Building Code, Residential (FBC--Residential)

2.0 LIMITATIONS

Simpson Strong-Tie® Titen Turbo™ Screw Anchors described in ER-712 complies with the 2020 and 2017 FBC--Building and the 2020 and 2017 FBC--Residential, subject to the following limitations:

1. The design and installation of the Titen Turbo™ Screw Anchors shall be in accordance with the 2018 or 2015 International Building Code and the 2018 or 2015 International Residential Code as noted in ER-712.
2. Load combinations shall be in accordance with Sections 1605.2 or 1605.3 of the FBC--Building, as applicable.
3. Design wind loads shall be in accordance with Section 1609.5 of the FBC--Building or Section R301.2.1.1 of the FBC--Residential, as applicable.
4. Use of Simpson Strong-Tie® Titen®2 Screw Anchors in applications exposed to the weather within High-velocity Hurricane Zones (HVHZ) as set forth in the

FBC--Building and the FBC--Residential is beyond the scope of this supplemental report.

5. Use of Simpson Strong-Tie® Titen Turbo™ Screw Anchors in High-velocity Hurricane Zones (HVHZ) as set forth in Section 2321.5.2 of the FBC--Building and Section 4409 of the FBC--Residential to resist wind uplift is permitted. The anchors shall be designed to resist the uplift forces as required in Section 1620 (HVHZ) of the FBC--Building or 700 pounds (3114 N), whichever is greater, per FBC--Building Section 2321.7.

For products falling under Florida Rule 61G20-3, verification that the report holder's quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission (or the building official when the report holder does not possess an approval by the Commission) is required to provide oversight and determine that the products are being manufactured as described in this evaluation report to establish continual product performance.

This supplement expires concurrently with ER-712.

For additional information about this evaluation report please visit www.uniform-es.org or email us at info@uniform-es.org