



Item Number:

T30S10470

1/7/2005

Product Description:

A fabric in a plain weave using .030" dia. vinyl coated two strains 1000 den. polyester core yarns in warp and fill.

Attribute	ASTM	Warp	Fill	Typical
Construction, end/inch	D3775-96	12.0	9.0	
Weight, oz/yd ²	D3776-96	--	--	13.2
Tensile Strength (grab), lbf	D5034-95	572.1	632.1	
Tensile Strength (strip), lbf	D5035-95	229.7	338.3	
Tear Strength, (Trapezodial), lbf	D1117-97	99.9	121.6	
Elongation, %	D5035-95	23.7	21.7	
Abrasion Resistance (H18/500 cycles/ with no add weight)	D3884-92	No exposure to core yarn		
Flammability Rating		CS 191-53 & CA 117 E		
Weatherability, 1200 hours	G53-96	No discoloration		
Mildew Resistance	G21-96	No growth		

** The above results are a representative of real data from single test samples.
Presently no specification is incorporated.