

PRODUCT EVALUATION REPORT	
Project No.: ACE-2026-157	Report No.: ACE-PER-1144, Rev. 1

Product Description: Style-Rib Exposed Fastener Metal Wall Panel

Product Manufacturer: Centria, 700 State Highway 121 Bypass, Suite 200, Lewisville, TX 75067

Code: Current Edition of the Florida Building Code including the 9th Edition (2026) Florida Building Code

Compliance Method: Product Approval Rule 61G20-3.005(1)(d) – Product Evaluation Report by a Licensed Professional Engineer

Product Category/Sub-Category: Structural Components/Structural Wall

SCOPE: Evaluate CENTRIA's Style-Rib Exposed Fastener Metal Wall Panel for conformance to the 9th Edition (2026) Florida Building Code excluding the High Velocity Hurricane Zone (HVHZ).

DESCRIPTION OF PRODUCT – INSTALLATION REQUIREMENTS:

See Reference 1 for a description of the product, its installation and other pertinent data related to its approved use.

CODE CONFORMANCE:

The 9th Edition (2026) Florida Building Code (FBC) requirements specific to this product that have been met by engineering evaluation (Reference 2.a) and depicted on the manufacturer's installation drawings (Reference 1) are the following.

- 1403.3 Exterior Walls – Wind Resistance
- 1404.5 Exterior Walls – Metal
- Table 1405.2 Minimum Thickness of Weather Coverings
 - Steel must meet or exceed 0.0149" in thickness.
- 1405.17 Exterior Walls - Fasteners
- Table 1604.3 Deflection Limits
 - Exterior Walls/Flexible Finishes, deflection for wind loading limited to L/120.
- 1609 Wind Loads
- 2210.1 Cold-Formed Steel, General

The engineering evaluation (Reference 2.a) is based on AISI S100-07/S2-10, North American Specification for the Design of Cold-formed Steel Structural Members. The engineering evaluation determines Wind Pressure Loading in PSF. Safety factors are as prescribed in AISI S100-07/S2-10. Fastener allowable is based on a safety factor of 3. Deflection limitation based on L/120.

See ACE-EER-1144 (Reference 2.b) for equivalency evaluation of AISI S100-07/S2-10.

LIMITATIONS AND CONDITIONS OF USE:

This product evaluation report contains or refers to specifications, technical details and installation details and/or methods that pertain to the proper use and/or installation of the product specified herein. Specific limitations and conditions of its use, including but not limited to the following, are contained in Reference 1 and are the subject of Product Approval in accordance with the State of Florida Product Approval Rule 61G20-3.

- Design Pressure Rating (psf)
- Installation substrate requirements.
- Installation anchor requirements.
- Installation restrictions.
- Product description.
- Product components.

REFERENCES & SUPPORTING DOCUMENTS:

- 1) Manufacturer's Installation Instructions:
 - a) Style-Rib Exposed Fastener Metal Wall Panel Installation Drawing, Signed and Sealed by Robert J. Amoruso, P.E.
 - b) Horizontal Exposed Fastener Installation Details, Signed and Sealed by Robert J. Amoruso, P.E.
 - c) Vertical Exposed Fastener Installation Details, Signed and Sealed by Robert J. Amoruso, P.E.
- 2) Reports and Calculations
 - a) Report No. ACE-PER-1144, Appendix 2 and 3, Panel Span Analysis for Centria Exposed Fastener Metal Wall Panels to AISI S100-07/S2-10, Signed and Sealed by Robert J. Amoruso, P.E.
 - b) Report No. ACE-EER-1144, Equivalency Evaluation Report for Centria Exposed Fastener Metal Wall Panels, Signed and Sealed by Robert J. Amoruso, P.E.
 - i) EER evaluates AISI S100-07/S2-10 used in Ref. 2.a above as compared to AISI S100-16(2020) w/S2-20 (9th Edition FBC).
- 3) 9th Edition (2026) Florida Building Code (FBC), Building Volume
 - a) 1403.3 Exterior Walls – Wind Resistance
 - b) 1404.5 Exterior Walls – Metal
 - c) Table 1405.2 Minimum Thickness of Weather Coverings
 - i) Steel must meet or exceed 0.0149" in thickness.
 - d) 1405.17 Exterior Walls - Fasteners
 - e) Table 1604.3 Deflection Limits
 - i) Exterior Walls/Flexible Finishes, deflection for wind loading limited to L/120.
 - f) 1609 Wind Loads
 - g) 2210.1 Cold-Formed Steel, General
- 4) Standards (used in design)
 - a) AISI S100-07/S2-10, North American Specification for the Design of Cold-formed Steel Structural Members


APPENDICES:

- Appendix 1: Style-Rib Exposed Fastener Metal Wall Panel Drawing, Section Properties, Configuration and Fastener Requirements, 1 sheet
- Appendix 2: Style-Rib Exposed Fastener Metal Wall Panel Load/Span Tables with 3/16" Girts, 4 Sheets
- Appendix 3: Style-Rib Exposed Fastener Metal Wall Panel Load/Span Tables with 16 GA. Girts, 4 Sheets

**Certificate of Independence per Product
Approval Rule 61G20-3.009**

Robert J. Amoruso, P.E., does not have, nor will he acquire, any financial interest in the company manufacturing or distributing product(s) covered by this Product Evaluation Report.

Robert J. Amoruso, P.E., does not have, nor will he acquire any financial interest in any other entity involved in the approval process or testing of the product(s) covered by this Product Evaluation Report.



Digitally
signed by

Robert J
Amoruso

Date:

2026.09.22

14:14:04

-04'00'


Evaluated by:
Robert J. Amoruso, P.E.
FL P.E. License No. 49752

APPENDIX 1

Style-Rib Exposed Fastener Metal Wall Panel Drawing, Section Properties, Configuration and Fastener Requirements

- Panel Material with a Minimum Yield Strength = 37 ksi
 - ASTM A 653/A 653M - Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process.
- Panel Configuration
 - 36" effective width with 5 ribs, each 1-1/2" high.
 - thicknesses
 - 24 gage (0.024")
 - 22 gage (0.030")
 - 20 gage (0.036")
 - 18 gage (0.049")
- Panel Installation Fasteners
 - 1/4" diameter (equivalent to #14) Sheet Metal Screws with 5/8" diameter combination washers.
 - Five screws are installed per panel at each support.

Style-Rib Exposed Fastener Metal Wall Panel Section Properties			
Thickness (GA.)	Minimum Ix (in ⁴ /ft)	Minimum Sx (in ³ /ft)	Weight (psf)
24	0.095	0.116	1.19
22	0.125	0.157	1.48
20	0.157	0.200	1.78
18	0.224	0.293	2.37



STYLE-RIB
VERTICAL APPLICATION OR
HORIZONTAL APPLICATION

STYLE-RIB SIDING / FASTENING SCHEDULE

WIND LOAD/SPAN TABLE FOR Style-Rib - 18 Ga.



5 Fasteners per Panel

Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.224 \text{ in}^4/\text{ft}$

$S_{min} = 0.293 \text{ in}^3/\text{ft}$

Deflection @ L/120

$F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	14.72 g	14.72 g	16.46 g	110	Stress	6.28 g	6.28 g	7.02 g
psf	Defl.	11.37	15.24	14.04	psf	Defl.	6.44	8.63	7.96
30	Stress	12.02 g	12.02 g	13.44 g	120	Stress	6.01 g	6.01 g	6.72 g
psf	Defl.	9.93	13.31	12.27	psf	Defl.	6.26	8.39	7.73
40	Stress	10.41 g	10.41 g	11.64 g	130	Stress	5.78 g	5.78 g	6.46 g
psf	Defl.	9.02	12.09	11.15	psf	Defl.	6.09	8.17	7.52
50	Stress	9.31 g	9.31 g	10.41 g	140	Stress	5.57 g	5.57 g	6.22 g
psf	Defl.	8.38	11.23	10.35	psf	Defl.	5.94	7.97	7.34
60	Stress	8.50 g	8.50 g	9.50 g	150	Stress	5.38 g	5.38 g	6.01 g
psf	Defl.	7.88	10.57	9.74	psf	Defl.	5.81	7.78	7.17
70	Stress	7.87 g	7.87 g	8.80 g	160	Stress	5.21 g	5.21 g	5.82 g
psf	Defl.	7.49	10.04	9.25	psf	Defl.	5.69	7.62	7.02
80	Stress	7.36 g	7.36 g	8.23 g	170	Stress	5.05 g	5.05 g	5.65 g
psf	Defl.	7.16	9.60	8.85	psf	Defl.	5.57	7.47	6.88
90	Stress	6.94 g	6.94 g	7.76 g	180	Stress	4.91 g	4.91 g	5.49 g
psf	Defl.	6.89	9.23	8.51	psf	Defl.	5.47	7.33	6.75
100	Stress	6.59 g	6.59 g	7.36 g	190	Stress	4.78 g	4.78 g	5.34 g
psf	Defl.	6.65	8.91	8.21	psf	Defl.	5.37	7.20	6.63

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 2.37 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. $\varnothing$ combination washers fastened to 3/16" minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 20 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.157 \text{ in}^4/\text{ft}$
 $S_{min} = 0.200 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	12.17 g	12.17 g	13.60 g	110	Stress	5.19 g	5.19 g	5.80 g
psf	Defl.	10.10	13.54	12.47	psf	Defl.	5.72	7.67	7.07
30	Stress	9.93 g	9.93 g	11.11 g	120	Stress	4.97 g	4.97 g	5.55 g
psf	Defl.	8.82	11.82	10.90	psf	Defl.	5.56	7.45	6.86
40	Stress	8.60 g	8.60 g	9.62 g	130	Stress	4.77 g	4.77 g	5.33 g
psf	Defl.	8.02	10.74	9.90	psf	Defl.	5.41	7.25	6.68
50	Stress	7.69 g	7.69 g	8.60 g	140	Stress	4.60 g	4.60 g	5.14 g
psf	Defl.	7.44	9.97	9.19	psf	Defl.	5.28	7.08	6.52
60	Stress	7.02 g	7.02 g	7.85 g	150	Stress	4.44 g	4.44 g	4.97 g
psf	Defl.	7.00	9.39	8.65	psf	Defl.	5.16	6.92	6.37
70	Stress	6.50 g	6.50 g	7.27 g	160	Stress	4.30 g	4.30 g	4.81 g
psf	Defl.	6.65	8.92	8.22	psf	Defl.	5.05	6.77	6.24
80	Stress	6.08 g	6.08 g	6.80 g	170	Stress	4.17 g	4.17 g	4.67 g
psf	Defl.	6.36	8.53	7.86	psf	Defl.	4.95	6.63	6.11
90	Stress	5.73 g	5.73 g	6.41 g	180	Stress	4.06 g	4.06 g	4.53 g
psf	Defl.	6.12	8.20	7.56	psf	Defl.	4.86	6.51	6.00
100	Stress	5.44 g	5.44 g	6.08 g	190	Stress	3.95 g	3.95 g	4.41 g
psf	Defl.	5.91	7.92	7.29	psf	Defl.	4.77	6.39	5.89

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.78 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. ϕ combination washers fastened to 3/16" minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 22 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$l_{min} = 0.125 \text{ in}^4/\text{ft}$
 $S_{min} = 0.157 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	10.78 g	10.78 g	12.05 g	110	Stress	4.60 g	4.60 g	5.14 g
psf	Defl.	9.36	12.55	11.56	psf	Defl.	5.30	7.11	6.55
30	Stress	8.80 g	8.80 g	9.84 g	120	Stress	4.40 g	4.40 g	4.92 g
psf	Defl.	8.18	10.96	10.10	psf	Defl.	5.15	6.90	6.36
40	Stress	7.62 g	7.62 g	8.52 g	130	Stress	4.23 g	4.23 g	4.73 g
psf	Defl.	7.43	9.96	9.18	psf	Defl.	5.02	6.72	6.20
50	Stress	6.82 g	6.82 g	7.62 g	140	Stress	4.07 g	4.07 g	4.55 g
psf	Defl.	6.90	9.24	8.52	psf	Defl.	4.89	6.56	6.04
60	Stress	6.22 g	6.22 g	6.96 g	150	Stress	3.94 g	3.94 g	4.40 g
psf	Defl.	6.49	8.70	8.02	psf	Defl.	4.78	6.41	5.91
70	Stress	5.76 g	5.76 g	6.44 g	160	Stress	3.81 g	3.81 g	4.26 g
psf	Defl.	6.17	8.26	7.61	psf	Defl.	4.68	6.27	5.78
80	Stress	5.39 g	5.39 g	6.03 g	170	Stress	3.70 g	3.70 g	4.13 g
psf	Defl.	5.90	7.90	7.28	psf	Defl.	4.59	6.15	5.67
90	Stress	5.08 g	5.08 g	5.68 g	180	Stress	3.59 g	3.59 g	4.02 g
psf	Defl.	5.67	7.60	7.00	psf	Defl.	4.50	6.03	5.56
100	Stress	4.82 g	4.82 g	5.39 g	190	Stress	3.50 g	3.50 g	3.91 g
psf	Defl.	5.47	7.34	6.76	psf	Defl.	4.42	5.92	5.46

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.48 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. ϕ combination washers fastened to 3/16" minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 24 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.095 \text{ in}^4/\text{ft}$
 $S_{min} = 0.116 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	9.26 g	9.26 g	10.36 g	110	Stress	3.95 g	3.93 b	4.42 g
	psf Defl.	8.54	11.45	10.55		psf Defl.	4.84	6.49	5.98
30	Stress	7.56 g	7.56 g	8.46 g	120	Stress	3.78 g	3.60 b	4.10 b
	psf Defl.	7.46	10.00	9.22		psf Defl.	4.70	6.30	5.81
40	Stress	6.55 g	6.55 g	7.32 g	130	Stress	3.63 g	3.33 b	3.78 b
	psf Defl.	6.78	9.09	8.37		psf Defl.	4.58	6.13	5.65
50	Stress	5.86 g	5.86 g	6.55 g	140	Stress	3.50 g	3.09 b	3.51 b
	psf Defl.	6.29	8.44	7.77		psf Defl.	4.47	5.99	5.52
60	Stress	5.35 g	5.35 g	5.98 g	150	Stress	3.38 g	2.88 b	3.28 b
	psf Defl.	5.92	7.94	7.32		psf Defl.	4.36	5.85	5.39
70	Stress	4.95 g	4.95 g	5.54 g	160	Stress	3.28 g	2.70 b	3.07 b
	psf Defl.	5.63	7.54	6.95		psf Defl.	4.27	5.72	5.28
80	Stress	4.63 g	4.63 g	5.18 g	170	Stress	3.18 g	2.54 b	2.89 b
	psf Defl.	5.38	7.21	6.65		psf Defl.	4.19	5.61	5.17
90	Stress	4.37 g	4.37 g	4.88 g	180	Stress	3.09 g	2.40 b	2.73 b
	psf Defl.	5.17	6.93	6.39		psf Defl.	4.11	5.50	5.07
100	Stress	4.14 g	4.14 g	4.63 g	190	Stress	3.01 g	2.28 b	2.59 b
	psf Defl.	5.00	6.70	6.17		psf Defl.	4.03	5.41	4.98

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.19 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. ϕ combination washers fastened to 3/16" minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 18 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.224 \text{ in}^4/\text{ft}$
 $S_{min} = 0.293 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	14.72 g	14.72 g	16.46 g	110	Stress	6.28 g	3.47 a	3.95 a
psf	Defl.	11.37	15.24	14.04	psf	Defl.	6.44	8.63	7.96
30	Stress	12.02 g	12.02 g	13.44 g	120	Stress	6.01 g	3.19 a	3.62 a
psf	Defl.	9.93	13.31	12.27	psf	Defl.	6.26	8.39	7.73
40	Stress	10.41 g	9.56 a	10.86 a	130	Stress	5.78 g	2.94 a	3.34 a
psf	Defl.	9.02	12.09	11.15	psf	Defl.	6.09	8.17	7.52
50	Stress	9.31 g	7.64 a	8.69 a	140	Stress	5.57 g	2.73 a	3.10 a
psf	Defl.	8.38	11.23	10.35	psf	Defl.	5.94	7.97	7.34
60	Stress	8.50 g	6.37 a	7.24 a	150	Stress	5.38 g	2.55 a	2.90 a
psf	Defl.	7.88	10.57	9.74	psf	Defl.	5.81	7.78	7.17
70	Stress	7.87 g	5.46 a	6.20 a	160	Stress	5.21 g	2.39 a	2.71 a
psf	Defl.	7.49	10.04	9.25	psf	Defl.	5.69	7.62	7.02
80	Stress	7.36 g	4.78 a	5.43 a	170	Stress	5.05 g	2.25 a	2.55 a
psf	Defl.	7.16	9.60	8.85	psf	Defl.	5.57	7.47	6.88
90	Stress	6.94 g	4.25 a	4.83 a	180	Stress	4.91 g	2.12 a	2.41 a
psf	Defl.	6.89	9.23	8.51	psf	Defl.	5.47	7.33	6.75
100	Stress	6.59 g	3.82 a	4.34 a	190	Stress	4.78 g	2.01 a	2.29 a
psf	Defl.	6.65	8.91	8.21	psf	Defl.	5.37	7.20	6.63

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 2.37 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. ϕ combination washers fastened to 16 Ga. minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 20 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.157 \text{ in}^4/\text{ft}$
 $S_{min} = 0.200 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	12.17 g	12.17 g	13.60 g	110	Stress	5.19 g	3.47 a	3.95 a
psf	Defl.	10.10	13.54	12.47	psf	Defl.	5.72	7.67	7.07
30	Stress	9.93 g	9.93 g	11.11 g	120	Stress	4.97 g	3.19 a	3.62 a
psf	Defl.	8.82	11.82	10.90	psf	Defl.	5.56	7.45	6.86
40	Stress	8.60 g	8.60 g	9.62 g	130	Stress	4.77 g	2.94 a	3.34 a
psf	Defl.	8.02	10.74	9.90	psf	Defl.	5.41	7.25	6.68
50	Stress	7.69 g	7.64 a	8.60 g	140	Stress	4.60 g	2.73 a	3.10 a
psf	Defl.	7.44	9.97	9.19	psf	Defl.	5.28	7.08	6.52
60	Stress	7.02 g	6.37 a	7.24 a	150	Stress	4.44 g	2.55 a	2.90 a
psf	Defl.	7.00	9.39	8.65	psf	Defl.	5.16	6.92	6.37
70	Stress	6.50 g	5.46 a	6.20 a	160	Stress	4.30 g	2.39 a	2.71 a
psf	Defl.	6.65	8.92	8.22	psf	Defl.	5.05	6.77	6.24
80	Stress	6.08 g	4.78 a	5.43 a	170	Stress	4.17 g	2.25 a	2.55 a
psf	Defl.	6.36	8.53	7.86	psf	Defl.	4.95	6.63	6.11
90	Stress	5.73 g	4.25 a	4.83 a	180	Stress	4.06 g	2.12 a	2.41 a
psf	Defl.	6.12	8.20	7.56	psf	Defl.	4.86	6.51	6.00
100	Stress	5.44 g	3.82 a	4.34 a	190	Stress	3.95 g	2.01 a	2.29 a
psf	Defl.	5.91	7.92	7.29	psf	Defl.	4.77	6.39	5.89

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.78 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. $\varnothing$ combination washers fastened to 16 Ga. minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 22 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.125 \text{ in}^4/\text{ft}$
 $S_{min} = 0.157 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	10.78 g	10.78 g	12.05 g	110	Stress	4.60 g	3.47 a	3.95 a
psf	Defl.	9.36	12.55	11.56	psf	Defl.	5.30	7.11	6.55
30	Stress	8.80 g	8.80 g	9.84 g	120	Stress	4.40 g	3.19 a	3.62 a
psf	Defl.	8.18	10.96	10.10	psf	Defl.	5.15	6.90	6.36
40	Stress	7.62 g	7.62 g	8.52 g	130	Stress	4.23 g	2.94 a	3.34 a
psf	Defl.	7.43	9.96	9.18	psf	Defl.	5.02	6.72	6.20
50	Stress	6.82 g	6.82 g	7.62 g	140	Stress	4.07 g	2.73 a	3.10 a
psf	Defl.	6.90	9.24	8.52	psf	Defl.	4.89	6.56	6.04
60	Stress	6.22 g	6.22 g	6.96 g	150	Stress	3.94 g	2.55 a	2.90 a
psf	Defl.	6.49	8.70	8.02	psf	Defl.	4.78	6.41	5.91
70	Stress	5.76 g	5.46 a	6.20 a	160	Stress	3.81 g	2.39 a	2.71 a
psf	Defl.	6.17	8.26	7.61	psf	Defl.	4.68	6.27	5.78
80	Stress	5.39 g	4.78 a	5.43 a	170	Stress	3.70 g	2.25 a	2.55 a
psf	Defl.	5.90	7.90	7.28	psf	Defl.	4.59	6.15	5.67
90	Stress	5.08 g	4.25 a	4.83 a	180	Stress	3.59 g	2.12 a	2.41 a
psf	Defl.	5.67	7.60	7.00	psf	Defl.	4.50	6.03	5.56
100	Stress	4.82 g	3.82 a	4.34 a	190	Stress	3.50 g	2.01 a	2.29 a
psf	Defl.	5.47	7.34	6.76	psf	Defl.	4.42	5.92	5.46

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.48 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. $\varnothing$ combination washers fastened to 16 Ga. minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12

WIND LOAD/SPAN TABLE FOR Style-Rib - 24 Ga.



5 Fasteners per Panel
Safety Factor = 3.00 (Fasteners)

$I_{min} = 0.095 \text{ in}^4/\text{ft}$
 $S_{min} = 0.116 \text{ in}^3/\text{ft}$

Deflection @ L/120
 $F_y = 37 \text{ ksi}$

Load		Single Span	Double Span	Triple Span	Load		Single Span	Double Span	Triple Span
20	Stress	9.26 g	9.26 g	10.36 g	110	Stress	3.95 g	3.47 a	3.95 a
psf	Defl.	8.54	11.45	10.55	psf	Defl.	4.84	6.49	5.98
30	Stress	7.56 g	7.56 g	8.46 g	120	Stress	3.78 g	3.19 a	3.62 a
psf	Defl.	7.46	10.00	9.22	psf	Defl.	4.70	6.30	5.81
40	Stress	6.55 g	6.55 g	7.32 g	130	Stress	3.63 g	2.94 a	3.34 a
psf	Defl.	6.78	9.09	8.37	psf	Defl.	4.58	6.13	5.65
50	Stress	5.86 g	5.86 g	6.55 g	140	Stress	3.50 g	2.73 a	3.10 a
psf	Defl.	6.29	8.44	7.77	psf	Defl.	4.47	5.99	5.52
60	Stress	5.35 g	5.35 g	5.98 g	150	Stress	3.38 g	2.55 a	2.90 a
psf	Defl.	5.92	7.94	7.32	psf	Defl.	4.36	5.85	5.39
70	Stress	4.95 g	4.95 g	5.54 g	160	Stress	3.28 g	2.39 a	2.71 a
psf	Defl.	5.63	7.54	6.95	psf	Defl.	4.27	5.72	5.28
80	Stress	4.63 g	4.63 g	5.18 g	170	Stress	3.18 g	2.25 a	2.55 a
psf	Defl.	5.38	7.21	6.65	psf	Defl.	4.19	5.61	5.17
90	Stress	4.37 g	4.25 a	4.83 a	180	Stress	3.09 g	2.12 a	2.41 a
psf	Defl.	5.17	6.93	6.39	psf	Defl.	4.11	5.50	5.07
100	Stress	4.14 g	3.82 a	4.34 a	190	Stress	3.01 g	2.01 a	2.29 a
psf	Defl.	5.00	6.70	6.17	psf	Defl.	4.03	5.41	4.98

Explanatory Notes For Load/Span Tables:

- Numbers in the tables indicate distance in feet between adjacent structural girts.
- Span length limitation factors:
Stress limitation uses $.6 \times F_y$ as design stress for wind load.
Deflection limitation uses span / 120.
- Panel weight = 1.19 psf.
- Load/Span tables are based on #14 fasteners with 5/8 in. ϕ combination washers fastened to 16 Ga. minimum thickness steel structural girts.
- Key to failure modes:
a - Fastener pullout from structural girt.
b - Fastener pullover.
g - Bending of panel.

12/28/12