

**SWARTZ**  
CONSULTING ENGINEERS LLC

|                 |                        |
|-----------------|------------------------|
| Project Number: | SCE 25-03015           |
| Project Name:   | Premium Atlantic Vinyl |
| Date:           | 3/21/2025              |
| Page:           | 1 of 15                |

## Product Approval Supporting Calculations Alternative Anchorage Analysis & Design

**Project Number:** SCE 25-03015


**Drawing Number:** D009458

**Reference Test Report:** NCTL 210-3914-1A

**Product Name:** Premium Atlantic Vinyl 36" X 72"

**Prepared for:**

Jeld-Wen Windows & Doors  
3737 Lakeport Blvd.  
Klamath Falls, OR



03/21/25

Prepared by:  
Swartz Consulting Engineers LLC


**Micah Swartz**

---

Micah Swartz, PE  
Florida License No. PE 93573  
Florida Registry No. 38420

This item has been digitally signed and sealed by Micah Swartz, P.E. on the date adjacent to the seal.

Printed copies of this document are not considered signed and sealed and the signature must be verified on any electronic copies.



**Scope:**

Swartz Consulting Engineers LLC is contracted by Jeld-Wen Windows & Doors to evaluate alternative anchorage for the product: Premium Atlantic Vinyl 36" X 72". This evaluation is based on testing performed by National Certified Testing Laboratories in Orlando, FL, test report no.: NCTL 210-3914-1A and dated 08/05/13.

This evaluation does not include the air infiltration, water resistance or water penetration of the installation method or the installed product. In addition, the design of the building substrate to resist the superimposed loads is by others.

**Reference Standards:**

*Florida Building Code, Building, 2023 Edition*

*ANSI/AWC NDS 2018 - National Design Specification (NDS) for Wood Construction*

*ANSI S100-16 (2020) North American Specification for the Design of Cold-Formed Steel Structural Members*

*ICC-ES Report ESR-1976 ITW Buildex TEKS Self-Drilling Fasteners*


*ICC-ES Report ESR-2196 Hilti Self Drilling Screws to connect cold-formed steel*

*NOA 24-0102.06 Tapcon Concrete and Masonry Anchors with Advanced Threadform Technology*

**Certification of Independence:**

In accordance with Rule 61G20-3 Florida Administrative Code, Swartz Consulting Engineers LLC hereby certifies the following:

- (1) Swartz Consulting Engineers LLC does not have, nor does it intend to acquire or will it acquire, a financial interest in any company manufacturing or distributing products tested or labeled by the
- (2) Swartz Consulting Engineers LLC is not owned, operated or controlled by any company manufacturing or distributing products it tests or labels.
- (3) Micah Swartz, P.E. does not have, nor will acquire, a financial interest in any company manufacturing or distributing products for which the reports are being issued.
- (4) Micah Swartz, P.E. does not have, nor will acquire, a financial interest in any other entity involved in the approval process of the product.



**Design Summary:**

The table below summarizes the product: Premium Atlantic Vinyl 36" X 72" and their corresponding performance levels as established by testing.

**Table 1: Summary of Test Results**

| Series/Model                     | Test Report Number             | Size (W x H) | Performance       |
|----------------------------------|--------------------------------|--------------|-------------------|
| Premium Atlantic Vinyl 36" X 72" | NCTL 210-3914-1A<br>(08/05/13) | 36" X 72"    | +50 psf / -50 psf |

**As Tested Design:**

Applied Load (psf): -50 psf Width: 36 in Height: 72 in Window Area: 18.0 ft<sup>2</sup>

Total Load: -900 lbs Number of Fasteners: 16 ft Load Per Fastener (Nailfin): -56 lbs  
Load Per Fastener (Thru Frame): -56 lbs

**Screw Information:**

Screw Size: 10 Screw Embed: 1.5 in Edge Distance: 3/4 in (minimum)

Wood Screw Withdrawal: 228 lbs Unity: 0.25  
Wood Screw Lateral: 149 lbs Unity: 0.38

**Alternative Fasteners:**

**Screw Information:**

Screw Size: 10 Screw Embed: 1.5 in Edge Distance: 3/4 in (minimum)


Wood Screw Withdrawal: 228 lbs Unity: 0.25  
Wood Screw Lateral: 149 lbs Unity: 0.38

**Nail Information:**

Nail Size: 6d Nail Type: Box Edge Distance: 3/4 in (minimum)

Total Load: -900 lbs Number of Nails: 24 Load Per Fastener (Nailfin): -38 lbs

Nail Withdrawal: 47 lbs Unity: 0.80  
Nail Lateral: 76 lbs Unity: 0.49



**Design Summary Continued:**

**TEK Screw Information:**

Screw Size: 10-16

TEK Withdrawal: 145 lbs

Unity: 0.39

TEK Lateral: 147 lbs

Unity: 0.38

**Tapcon Information:**


Tapcon Size: 3/16 Embedment: 1-1/4 in (minimum) Edge Distance: 2-1/2 in (minimum)

Tapcon Lateral (Concrete): 155 lbs

Unity: 0.36

Tapcon Lateral (CMU): 135 lbs

Unity: 0.42




### Summary of Test Results - Plastics Checklist

**Table 2:** Summary of Test Results - Plastics Checklist

| Product             | Test Report Number | Test Standard                     | Performance        |
|---------------------|--------------------|-----------------------------------|--------------------|
| White PVC 1476 5110 | P6504.04-106-18 R0 | ASTM D638 (before and after G155) | +9.5%              |
|                     |                    | ASTM D1929                        | 824 °F (440 °C)    |
|                     |                    | ASTM D2843                        | 71.8               |
|                     |                    | ASTM D635                         | Classification CC1 |
|                     |                    | ASTM 256                          | -3.3%              |
| White PVC 1476 5290 | P6504.04-106-18 R0 | ASTM D638 (before and after G155) | +9.5%              |
|                     |                    | ASTM D1929                        | 806 °F (430 °C)    |
|                     |                    | ASTM D2843                        | 72.6               |
|                     |                    | ASTM D635                         | Classification CC1 |
|                     |                    | ASTM 256                          | -35.5%             |

The testing summarized in the table above was conducted by Intertek in York, PA dated 08/23/23 and meets the requirements listed in Miami-Dade County Checklist #0445, For the approval of: Plastic and Foam Plastic.

The Saflex FlySafe 3D interlayer meets the requirements listed in Miami-Dade County Checklist #0445, For the approval of: Plastic and Foam Plastic as shown by NOA 23-0713.19



**Subject:** As Tested - Wood Screw Withdrawal

Input:

Calculation:

**Screw Information:**

Screw Size: 10

Root Diameter: 0.152 in

Screw Embed: 1.5 in

Main Member Type: S-P-F

G: 0.42

F<sub>em</sub>: 3,350 psi

$$W' = W * C_D * C_M^2 * C_t - \text{As per table 11.3.1 NDS 2018}$$

C<sub>D</sub>: 1.6 Load Duration Factor - Table 2.3.2 (NDS 2018)


C<sub>M</sub>: 1.0 Wet Service Factor - Table 11.3.3 (NDS 2018)

C<sub>t</sub>: 1.0 Temperature Factor - Table 11.3.4 (NDS 2018)

W: 95 lbs/in - Table 12.2B (NDS 2018)

W: 143 lbs

W': 228 lbs



**Subject:** As Tested - Wood Screw Lateral Design - Single Shear

Input:   
Calculation:

**Screw Information:**

Screw Size:  Root Diameter:  in  
Screw Embed:  in

Main Member Type:  G:   $F_{em}$ :  psi thickness ( $t_m$ ):  in

Side Member Type:  G:   $F_{es}$ :  psi thickness ( $t_s$ ):  in

**Lateral Design Factors - Table 12.3.1A (NDS 2018)**

|            |                                        |                                           |
|------------|----------------------------------------|-------------------------------------------|
| D:         | <input type="text" value="0.152"/> in  | Diameter                                  |
| $F_{yb}$ : | <input type="text" value="90"/> ksi    | Dowel Bending Yield Strength              |
| $F_{em}$ : | <input type="text" value="3,350"/> psi | Main Member dowel bearing strength        |
| $F_{es}$ : | <input type="text" value="3,350"/> psi | Side Member dowel bearing strength        |
| $l_m$ :    | <input type="text" value="1.5"/> in    | Main Member dowel bearing length          |
| $l_s$ :    | <input type="text" value="1.25"/> in   | Side Member dowel bearing length          |
| $R_d$ :    | <input type="text" value="2.2"/>       | Reduction term - Table 12.3.1B (NDS 2018) |
| $R_e$ :    | <input type="text" value="1"/>         | $= F_{em}/F_{es}$                         |
| $R_t$ :    | <input type="text" value="1.2"/>       | $= l_m/l_s$                               |
| $k_1$ :    | <input type="text" value="0.459"/>     | See Table                                 |
| $k_2$ :    | <input type="text" value="1.133"/>     | See Table                                 |

**Reference Lateral Design Values - Table 12.3.1A (NDS 2018)**

$Z_{Im}$ :  lbs  $Z_{Im} = \frac{D l_m F_{em}}{R_d}$  (EQ 12.3 - 1)


$Z_{II}$ :  lbs  $Z_{II} = \frac{k_1 D l_s F_{es}}{R_d}$  (EQ 12.3 - 3)

$Z_{III_m}$ :  lbs  $Z_{III_m} = \frac{k_2 D l_m F_{em}}{(1 + 2R_e)R_d}$  (EQ 12.3 - 4)

$Z_{IV}$ :  lbs  $Z_{IV} = \frac{D^2}{R_d} \sqrt{\frac{2F_{em}F_{yb}}{3(1 + R_e)}}$  (EQ 12.3 - 6)

$Z_{MIN}$ :  lbs

Note: Side member is part of the Jeld-Wen assembly and verified during testing. Modes  $Z_{Is}$  and  $Z_{III_s}$  are not applicable to the calculation.



**Subject:** As Tested - Wood Screw Lateral Design - Single Shear Cont.

### Adjusted Lateral Design Values

$$Z' = Z * C_D * C_M * C_t * C_g * C_{\Delta} - \text{As per table 11.3.1 NDS 2018}$$

|                |     |                                                 |
|----------------|-----|-------------------------------------------------|
| $C_D$ :        | 1.6 | Load Duration Factor - Table 2.3.2 (NDS 2018)   |
| $C_M$ :        | 1.0 | Wet Service Factor - Table 11.3.3 (NDS 2018)    |
| $C_t$ :        | 1.0 | Temperature Factor - Table 11.3.4 (NDS 2018)    |
| $C_g$ :        | 1.0 | Group Action Factor - Section 11.3.6 (NDS 2018) |
| $C_{\Delta}$ : | 1.0 | Geometry Factor - Section 12.5.1.1 (NDS 2018)   |

$$Z': \boxed{168} \text{ lbs}$$

### Fastener Bending Across Shim Space

|            |       |                                  |
|------------|-------|----------------------------------|
| $\Omega$ : | 1.67  |                                  |
| L:         | 0.25  | in Maximum Shim Gap              |
| D:         | 0.152 | in Diameter                      |
| $F_{yb}$ : | 90    | ksi Dowel Bending Yield Strength |

$$\frac{F_{yb}}{\Omega} = \frac{M}{S} = \frac{16ZL}{\pi D^3} \Leftrightarrow Z = \frac{F_{yb} \pi D^3}{16 \Omega L}$$

$$\text{Where } M = \frac{ZL}{2} \text{ (Guided Bending)}$$


$$Z_n/\Omega: \boxed{149} \text{ lbs}$$

### Bearing on Masonry Strap

|            |       |                               |
|------------|-------|-------------------------------|
| $\Omega$ : | 3.00  |                               |
| $F_u$ :    | 33    | ksi Tensile Strength of strap |
| t:         | 20    | GA                            |
| t:         | 0.036 | in thickness of strap         |
| D:         | 0.152 | in                            |

$$\frac{P_{nv}}{\Omega} = 2.7 * t * D * F_u - (EQ. J4.3.1 - 4, AISI S100)$$

$$P_{nv}/\Omega: \boxed{162} \text{ lbs}$$



Subject: Nail Withdrawal

Input:

Calculation:

**Nail Information:**

Nail Size: 6d

Nail Length: 2 in

Nail Type: Box

Nail Diameter: 0.099 in

Nail Embedment: 1.88 in

Main Member Type: S-P-F

G: 0.42

$F_{em}$ : 3,350 psi

thickness ( $t_m$ ): 1.5 in

Side Member Type: PVC

G: N/A

$F_{es}$ : 13,750 psi

thickness ( $t_s$ ): 0.125 in

$$W' = W * C_D * C_M^2 * C_t - \text{As per table 11.3.1 NDS 2018}$$

$C_D$ : 1.6 Load Duration Factor - Table 2.3.2 (NDS 2018)

$C_M$ : 1.0 Wet Service Factor - Table 11.3.3 (NDS 2018)


$C_t$ : 1.0 Temperature Factor - Table 11.3.4 (NDS 2018)

W: 16 lbs/in

$$W = 1380G^{5/2}D - \text{Carbon Steel Nails (EQ. 12.2 - 3, NDS 2018)}$$

W: 29 lbs

W': 47 lbs



**Subject:** Nail Lateral Design - Single Shear

Input:   
Calculation:

**Nail Information:**

Nail Size:  Nail Length:  in  
Nail Type:  Nail Diameter:  in Nail Embedment:  in

Main Member Type:  G:   $F_{em}$ :  psi thickness ( $t_m$ ):  in

Side Member Type:  G:   $F_{es}$ :  psi thickness ( $t_s$ ):  in

**Lateral Design Factors - Table 12.3.1A (NDS 2018)**

|            |                                         |                                           |
|------------|-----------------------------------------|-------------------------------------------|
| D:         | <input type="text" value="0.099"/> in   | Diameter                                  |
| $F_{yb}$ : | <input type="text" value="100"/> ksi    | Dowel Bending Yield Strength              |
| $F_{em}$ : | <input type="text" value="3,350"/> psi  | Main Member dowel bearing strength        |
| $F_{es}$ : | <input type="text" value="13,750"/> psi | Side Member dowel bearing strength        |
| $l_m$ :    | <input type="text" value="1.625"/> in   | Main Member dowel bearing length          |
| $l_s$ :    | <input type="text" value="0.125"/> in   | Side Member dowel bearing length          |
| $R_d$ :    | <input type="text" value="2.2"/>        | Reduction term - Table 12.3.1B (NDS 2018) |
| $R_e$ :    | <input type="text" value="0.2436"/>     | $= F_{em}/F_{es}$                         |
| $R_t$ :    | <input type="text" value="13.0"/>       | $= l_m/l_s$                               |
| $k_1$ :    | <input type="text" value="1.230"/>      | See Table                                 |
| $k_2$ :    | <input type="text" value="0.612"/>      | See Table                                 |

**Reference Lateral Design Values - Table 12.3.1A (NDS 2018)**

$Z_{Im}$ :  lbs  $Z_{Im} = \frac{D l_m F_{em}}{R_d}$  (EQ 12.3 - 1)


$Z_{II}$ :  lbs  $Z_{II} = \frac{k_1 D l_s F_{es}}{R_d}$  (EQ 12.3 - 3)

$Z_{III_m}$ :  lbs  $Z_{III_m} = \frac{k_2 D l_m F_{em}}{(1 + 2R_e) R_d}$  (EQ 12.3 - 4)

$Z_{IV}$ :  lbs  $Z_{IV} = \frac{D^2}{R_d} \sqrt{\frac{2F_{em}F_{yb}}{3(1 + R_e)}}$  (EQ 12.3 - 6)

$Z_{MIN}$ :  lbs

Note: Side member is part of the Jeld-Wen assembly and verified during testing. Modes  $Z_{Is}$  and  $Z_{III_s}$  are not applicable to the calculation.



**Subject:** Nail Lateral Design - Single Shear Cont.

### Adjusted Lateral Design Values

$$Z' = Z * C_D * C_M * C_t * C_g * C_{\Delta} - \text{As per table 11.3.1 NDS 2018}$$

|                |     |                                                 |
|----------------|-----|-------------------------------------------------|
| $C_D$ :        | 1.6 | Load Duration Factor - Table 2.3.2 (NDS 2018)   |
| $C_M$ :        | 1.0 | Wet Service Factor - Table 11.3.3 (NDS 2018)    |
| $C_t$ :        | 1.0 | Temperature Factor - Table 11.3.4 (NDS 2018)    |
| $C_g$ :        | 1.0 | Group Action Factor - Section 11.3.6 (NDS 2018) |
| $C_{\Delta}$ : | 1.0 | Geometry Factor - Section 12.5.1.1 (NDS 2018)   |

$$Z': \boxed{96} \text{ lbs}$$

### Fastener Bending Across Shim Space

|            |       |                                  |
|------------|-------|----------------------------------|
| $\Omega$ : | 1.67  |                                  |
| L:         | 0.25  | in Maximum Shim Gap              |
| D:         | 0.099 | in Diameter                      |
| $F_{yb}$ : | 100   | ksi Dowel Bending Yield Strength |

$$\frac{F_{yb}}{\Omega} = \frac{M}{S} = \frac{16ZL}{\pi D^3} \Leftrightarrow Z = \frac{F_{yb}\pi D^3}{16\Omega L}$$

$$\text{Where } M = \frac{ZL}{2} \text{ (Guided Bending)}$$


$$Z_n/\Omega: \boxed{76} \text{ lbs}$$

### Bearing on Masonry Strap

|            |       |                               |
|------------|-------|-------------------------------|
| $\Omega$ : | 3.00  |                               |
| $F_u$ :    | 33    | ksi Tensile Strength of strap |
| t:         | 20    | GA                            |
| t:         | 0.036 | in thickness of strap         |
| D:         | 0.099 | in                            |

$$\frac{P_{nv}}{\Omega} = 2.7 * t * D * F_u - (EQ. J4.3.1 - 4, AISI S100)$$

$$P_{nv}/\Omega: \boxed{106} \text{ lbs}$$



Subject: TEK Withdrawal

Input:   
Calculation:

**Shear Strength of Fastener - ESR 1976**

Screw Size: 10-16

$P_{nv}/\Omega$ : 885 lbs See ESR 2196

**Tensile Pullout - ESR 1976**

Screw Size: 10-16

$F_u$ : 45 ksi

$t$ : 16 GA

$t$ : 0.0598 in

Tensile Strength of material NOT in contact with screw head

Thickness of material NOT in contact with screw head

$P_{nv}/\Omega$ : 145 lbs See ESR 2196

**Tensile Pullover**

Note: The tensile pullover analysis checks the material IN contact with the screw head. This material is part of the Jeld-Wen assembly and has been verified by testing. Below is a check to ensure the head size of the TEK screw is equal to or larger than the head of the tested fastener, ensuring compliance.


**Tested Fastener Head Size:**

Screw Size: 8  
Head Size: 0.312 in

Tested fastener is a

**TEK Screw Head Size:**

Screw Size: 10-16  
Head Size: 0.365 in



Subject: TEK Lateral Design

Input:   
Calculation:

### Shear Strength of Fastener - ESR 1976

Screw Size: 10-16

$P_{nv}/\Omega$ : 573 lbs See ESR 2196

### Bearing Strength of Material NOT in Contact with Screw Head - AISI S100

Screw Size: 10-16

$\Omega$ : 3.00

D: 0.138 in Root Diameter of TEK Screw  
 $F_u$ : 45 ksi Tensile Strength of material NOT in contact with screw head  
t: 18 GA  
t: 0.0478 in Thickness of material NOT in contact with screw head

$$\frac{P_{nv1}}{\Omega} = 2.7 * t * D * F_u - (EQ.J4.3.1 - 3, AISI S100)$$

$$\frac{P_{nv2}}{\Omega} = 4.2 \sqrt{t^3 * D} * F_u - (EQ.J4.3.1 - 1, AISI S100)$$

$P_{nv1}/\Omega$ : 267 lbs

$P_{nv2}/\Omega$ : 245 lbs

$P_{nv}/\Omega$ : 245 lbs  $\frac{P_{nv}}{\Omega} = \text{smallest of } \frac{P_{nv1}}{\Omega} \text{ and } \frac{P_{nv2}}{\Omega}$

### Bearing Strength of Material IN in Contact with Screw Head

Note: Material IN contact with the screw head is part of the Jeld-Wen assembly and has been verified by testing.

### Fastener Bending Across Shim Space


L: 0.25 in Maximum Shim Gap  
D: 0.138 in Root Diameter of TEK Screw  
 $F_{yb}$ : 100 ksi Yield Strength of TEK Screw

$\Omega$ : 3.00

$$\frac{F_{yb}}{\Omega} = \frac{M}{S} = \frac{16P_n L}{\pi D^3} \Leftrightarrow P_n = \frac{F_{yb} \pi D^3}{16 \Omega L}$$

Where  $M = \frac{P_n L}{2}$  (Guided Bending)

$P_n/\Omega$ : 206 lbs



**Bearing Strength of Masonry Straps - AISI S100**

Screw Size: 10-16

TEK Screw

$\Omega$ : 3.00

D: 0.138 in

Root Diameter of TEK Screw

$F_u$ : 33 ksi

Tensile Strength of Masonry Strap


t: 20 GA

t: 0.0359 in

Thickness of Masonry Strap

$$\frac{P_{nv}}{\Omega} = 2.7 * t * D * F_u - (EQ. J4.3.1 - 3, AISI S100)$$

$P_{nv}/\Omega$ : 147 lbs



Subject: Tapcon Lateral Design

Input:   
Calculation:

**Tapcon Size:**

Size:   
D:  in Nominal Diameter  
D<sub>sh</sub>:  in Shank Diameter

**Fastener Shear Capacity - 3,000 psi Concrete**

P<sub>nv</sub>/Ω:  lbs See Table 1B of NOA 24-0102.06

**Fastener Shear Capacity - Medium-Weight CMU**

P<sub>nv</sub>/Ω:  lbs See Table 3 of NOA 24-0102.06

**Note:**

- Critical anchor spacing is 16D
- Minimum Anchor Embedment is 1-1/4"
- Minimum Edge Distance is 2-1/4"

**Fastener Bending Across Shim Space**

L:  in Maximum Shim Gap  
D<sub>sh</sub>:  in Shank Diameter of Tapcon  
F<sub>yb</sub>:  ksi Yield Strength of Tapcon

Ω:

$$\frac{F_{yb}}{\Omega} = \frac{M}{S} = \frac{16P_n L}{\pi D^3} \Leftrightarrow P_n = \frac{F_{yb} \pi D^3}{16 \Omega L}$$

Where  $M = \frac{P_n L}{2}$  (Guided Bending)

P<sub>n</sub>/Ω:  lbs

**Bearing Strength of Masonry Straps - AISI S100**

Size:  Tapcon Size  
D<sub>sh</sub>:  in Shank Diameter of Tapcon Screw  
F<sub>u</sub>:  ksi Tensile Strength of Masonry Strap  
t:  GA  
t:  in Thickness of Masonry Strap

Ω:

$$\frac{P_{nv}}{\Omega} = 2.7 * t * D * F_u - (EQ. J4.3.1 - 3, AISI S100)$$

P<sub>nv</sub>/Ω:  lbs